

ExxonMobil™ PP3155

Polypropylene Homopolymer

Product Description

A homopolymer resin designed for spunbond nonwovens. The resin is particularly suited for excellent spinning for uniform, high quality fabrics.

General

Availability ¹	• North America	• South America
Features	• Good Processability	
Uses	• Fibers • Industrial Applications	• Medical/Healthcare Applications • Personal Care • Spunbond Nonwovens
Appearance	• Natural Color	
Form(s)	• Pellets	
Processing Method	• Filament Extrusion	• Spunbond Nonwovens
Revision Date	• November 2010	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	36 g/10 min	36 g/10 min	ASTM D1238
Density	0.9 g/cm³	0.9 g/cm³	ExxonMobil Method

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

Notes

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

Worldwide and the Americas

ExxonMobil Chemical Company
13501 Katy Freeway
Houston, TX 77079-1398
USA
1-281-870-6050

Asia Pacific

ExxonMobil Chemical Asia Pacific
1 HarbourFront Place
#06-00 HarbourFront Tower One
Singapore 098633
+66-2-1638699

Europe, Middle East and Africa

ExxonMobil Chemical Europe
Hermeslaan 2
1831 Machelen, Belgium
420-239-016-274

Typical properties: these are not to be construed as specifications.

©2014 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.