

Acrypet® IR D30

Polymethyl Methacrylate Acrylic
Mitsubishi Rayon America Inc.

General			
Material Status	• Commercial: Active		
Availability	• North America		
Features	• Good Chemical Resistance • Good Impact Resistance	• Good Weather Resistance • High Clarity	• High Hardness • Pleasing Surface Appearance
Uses	• Appliances • Automotive Applications	• Electrical/Electronic Applications • Optical Applications	
Forms	• Pellets		

Physical	Nominal Value Unit	Test Method
Specific Gravity	1.17 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.6 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.70 %	ASTM D955
Water Absorption (24 hr)	0.40 %	ASTM D570

Mechanical	Nominal Value Unit	Test Method
Tensile Strength ²	51.0 MPa	ASTM D638
Tensile Elongation ² (Break)	80 %	ASTM D638
Flexural Modulus (6.35 mm)	2250 MPa	ASTM D790
Flexural Strength (6.35 mm)	78.6 MPa	ASTM D790

Impact	Nominal Value Unit	Test Method
Notched Izod Impact (6.35 mm)	20 J/m	ASTM D256

Hardness	Nominal Value Unit	Test Method
Rockwell Hardness (M-Scale)	65	ASTM D785

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	86.0 °C	ASTM D648
Vicat Softening Temperature	101 °C	ASTM D1525
CLTE - Flow	0.000080 cm/cm/°C	ASTM D696

Optical	Nominal Value Unit	Test Method
Refractive Index	1.490	ASTM D542
Transmittance (3200 µm)	92.0 %	ASTM D1003

Additional Information	
Surface Resistivity, JIS K6911: >10 ¹⁶ ohm	
Volume Resistivity, JIS K6911: >10 ¹⁵ ohm-cm	
Dielectric Breakdown Strength: 18 kV/mm	
Dielectric Constant, 60Hz: 3.8	
Dielectric Loss Tangent, 60Hz: 0.04	
Arc Resistance, JIS K6911: No Trace	

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type I