

Catalloy

Product Description

Adflex Q 300 F is a thermoplastic polyolefin which has been developed for the extrusion or calendering of soft film. Adflex Q 300 F can also be used as impact/toughener modifier of polypropylene homopolymer in extrusion applications. In strapping applications for instance, it notably decreases fibrillation and improves the processability of the film at high drawing ratios. Adflex Q 300 F can be processed on any conventional PP extrusion line as well as on PVC calendars. It can also be blown on standard LDPE or LLDPE film lines.

Regulatory Status

For regulatory compliance information, see Adflex Q 300 F [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America; South & Central America
Application	Agriculture Film; Bags & Pouches; Bottles For Consumer Goods; Bottles for Industrial Use; Collapsible Tubes; Film Wrap; Heavy Duty Packaging; Hygiene Film; Lamination Film; Peelable Film; Surface Protection Film
Market	Compounding; Flexible Packaging; Rigid Packaging
Processing Method	Blown Film; Extrusion Blow Molding; Sheet and Profile Extrusion
Attribute	Good Flexibility

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	0.8	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.88	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	330	MPa	ISO 178
Tensile Stress at Break	13	MPa	ISO 527-1, -2
Tensile Stress at Yield	9	MPa	ISO 527-1, -2
Tensile Strain at Break	550	%	ISO 527-1, -2
Tensile Strain at Yield	35	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	70	kJ/m ²	ISO 179
(-20 °C)	100	kJ/m ²	ISO 179
(-40 °C)	100	kJ/m ²	ISO 179
Hardness			
Shore Hardness, (Shore D)	36		ISO 868
Thermal			
Vicat Softening Temperature, (A50)	78	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	50	°C	ISO 75B-1, -2
Melting Temperature	163	°C	ISO 11357-3
Optical			

Haze	95 %	ASTM D1003
Gloss, (45°, 50 µm)	4	ASTM D2457

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.