

Catalloy

Product Description

Adflex X 190 G is a reactor TPO (thermoplastic polyolefin) manufactured using the LyondellBasell's proprietary Catalloy process technology.

It has been developed as an impact modifier for polypropylene to be used both in extrusion and in injection moulding applications. Thanks to its particular characteristics, it does not alter the transparency of the modified polypropylene (homopolymer or random copolymer). Adflex X 190 G exhibits a high softness and a low modulus, with a relatively high Melt Flow Index. It does not contain any slip nor anti-blocking agents. The grade is available in natural pellet form.

Regulatory Status

For regulatory compliance information, see Adflex X 190 G [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America; South & Central America
Application	Crates; Hot Melt Adhesives; Housewares; Impact Modification; Industrial Packaging; Peelable Film; Sports, Leisure & Toys
Market	Consumer Products; Flexible Packaging
Processing Method	Compounding; Injection Molding
Attribute	Good Flexibility; Good Processability; Low Temperature Impact Resistance; Medium Flow; Soft

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ISO 1133-1
Density	0.88	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	80	MPa	ISO 178
Tensile Stress at Break	12	MPa	ISO 527-1, -2
Tensile Strain at Break	600	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	NB	kJ/m ²	ISO 179
(-20 °C)	NB	kJ/m ²	ISO 179
(-40 °C)	4	kJ/m ²	ISO 179
Hardness			
Shore Hardness, (Shore D, 15 sec)	30		ISO 868
Thermal			
Vicat Softening Temperature, (A50)	56	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	40	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.