

Alathon® M6210

High Density (MMW) Polyethylene

LyondellBasell Industries

Technical Data

Product Description

ALATHON M 6210 is a medium molecular weight high density homopolymer. Typical applications for this resin are blown film, coextrusion and low WVTR.

General

Features	• Food Contact Acceptable	• Homopolymer	• Medium Molecular Weight
Uses	• Film		
Agency Ratings	• FDA 21 CFR 177.1520		
Forms	• Pellets		
Processing Method	• Blown Film	• Coextrusion	

Physical	Nominal Value Unit	Test Method
Density	0.958 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.95 g/10 min	ASTM D1238

Films	Nominal Value Unit	Test Method
Secant Modulus		ASTM D882
MD	938 MPa	
TD	1270 MPa	
Tensile Strength		ASTM D882
MD: Yield	26.9 MPa	
TD: Yield	27.6 MPa	
MD: Break	54.5 MPa	
TD: Break	23.4 MPa	
Tensile Elongation		ASTM D882
MD: Break	700 %	
TD: Break	750 %	
Elmendorf Tear Strength		ASTM D1922
MD	25 g	
TD	1100 g	

Extrusion	Nominal Value Unit
Melt Temperature	199 to 210 °C

Extrusion Notes

Typical Extrusion Conditions
2.0 mil Blown Film
Blow Up Ratio: 2.5:1
Die Gap: 60 mil

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.