

Styrolux® 693D is a clear styrene-butadiene copolymer (SBC) with a well balanced combination of toughness and clarity. Styrolux® 693D is mainly used for thermoformed articles, especially in blends with general-purpose polystyrene. Styrolux® 693D contains a microcrystalline wax which acts as an antiblock providing processing benefits but decreases the printability.

Major applications include: food and non-food packagings, thermoformed transparent containers and cups for cold beverages, thermoformed lids, toys, boxes.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	12.5	cm ³ /10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1300	MPa	ISO 527
Yield stress	22	MPa	ISO 527
Yield strain	2.2	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Tensile creep modulus, 1000h	490	MPa	ISO 899-1
Charpy impact strength (+23°C)	no break	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	59	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	72	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	48	°C	ISO 306
Coeff. of linear therm. expansion, parallel	75	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	UL 94
Thickness tested	1.5	mm	-
Burning behav. at thickness h	HB	class	UL 94
Thickness tested	3.2	mm	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	2.5	-	IEC 62631-2-1
Relative permittivity, 1MHz	2.5	-	IEC 62631-2-1
Dissipation factor, 100Hz	3	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	8	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Comparative tracking index	600	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water absorption	0.07	%	Sim. to ISO 62
Humidity absorption	0.07	%	Sim. to ISO 62
Density	1010	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	230	°C	ISO 294
Injection Molding, mold temperature	50	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Characteristics

Processing

Injection Molding, Film Extrusion, Sheet Extrusion, Other Extrusion,
Blow Molding

Injection Molding

PROCESSING

injection molding, Melt temperature, range: 180 - 250 °C

injection molding, Mold temperature, range: 20 - 40 °C

Film extrusion

PROCESSING

Extrusion, Blown film, Melt temperature: 180 °C

Extrusion, Flat film, Melt temperature: 190 - 230 °C

Other extrusion

PROCESSING

Extrusion, Pipes, Melt temperature: 230 °C

Sheet extrusion

PROCESSING

Extrusion, Plates, Melt temperature: 190 °C

Disclaimer

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.