

Altuglas® DRT MATT 101

Polymethyl Methacrylate Acrylic

Altuglas International of Arkema Inc.

General		
Material Status	• Commercial: Active	
Availability	• Asia Pacific	• Europe
Appearance	• Matte Finish	
Forms	• Granules	
Physical	Nominal Value Unit	Test Method
Density	1.15 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	1.6 g/10 min	ISO 1133
Molding Shrinkage - Flow	0.20 to 0.80 %	ASTM D955
Water Absorption (Equilibrium, 23°C, 50% RH)	0.36 %	ISO 62
Mechanical	Nominal Value Unit	Test Method
Tensile Stress (Yield, 23°C)	45.0 MPa	ISO 527-2
Tensile Strain (Break, 23°C)	45 %	ISO 527-2
Flexural Modulus (23°C)	1850 MPa	ISO 178
Flexural Strength (23°C)	69.0 MPa	ISO 178
Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0 kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength (23°C)	60 kJ/m ²	ISO 179/2U
Notched Izod Impact Strength (23°C)	5.0 kJ/m ²	ISO 180/1A
Thermal	Nominal Value Unit	Test Method
Heat Deflection Temperature 1.8 MPa, Unannealed	90.0 °C	ISO 75-2/A
Vicat Softening Temperature	98.0 °C	ISO 306/B
Flammability	Nominal Value Unit	Test Method
Flame Rating - UL	HB	UL 94
Optical	Nominal Value Unit	Test Method
Refractive Index ²	1.490	ISO 489
Transmittance	90.0 %	ASTM D1003
Injection	Nominal Value Unit	
Drying Temperature	80.0 to 85.0 °C	
Drying Time	2.0 to 4.0 hr	
Processing (Melt) Temp	235 to 255 °C	
Mold Temperature	70.0 to 80.0 °C	

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method B