



Elastomeric Material Solutions Division
 1100 Governor Lea Road, Bear, DE 19701
 (302) 834-2100 (302) 834-4021 (Fax)
www.rogerscorp.com/arlton

PRODUCT INFORMATION SHEET

ARLON® Product Number 32570XA015

PRODUCT DESCRIPTION

Design / Construction

Interleave: 0.0025" polyethylene
Side 1: Uncured Silicone Rubber
Carrier: 0.005" release PET (nominal)

Rubber Add-On Thickness	Value	Tolerance	Method
Overall Thickness:	0.015"	±0.0015"	Arlon SQA-TMS-003
Product Color :	Grey		

TYPICAL PROPERTIES

Silicone Properties	Value	Method
Tensile Strength psi	1100	Arlon SQA-TMS-008
Elongation %	650	Arlon SQA-TMS-008
Tear Strength (Die B) ppiw	83	Arlon SQA-TMS-029
Durometer Shore A Points	44	Arlon SQA-TMS-014
Specific Gravity ---	1.24	Arlon SQA-TMS-024
Carrier Properties	Value	Method
Thickness	0.005"	Arlon SQA-TMS-003
Color	Translucent	N/A
Product Properties	Value	Method
Flame Resistance --	UL94V-0	Arlon SQA-TMS-019
Total Product Weight oz/yd ²	13.9	Arlon SQA-TMS-025

SHELF LIFE & PROCESSING RECOMMENDATIONS

Product Shelf Life	6 months from date of manufacture @ 70°F
<i>Note: Shelf life is defined as the duration of time for which the product will meet the physical characteristics outlined on this page. It does not guarantee the product's usefulness in all applications.</i>	
Recommended Cure Cycle	15 minutes @ 350°F and 50 psi
Recommended Postcure Cycle	400°F for 2 hours
Product Operating Temperature	-70°F to 400°F

UL INFORMATION

UL Recognition : 220°C Electrical/ 200°C Mechanical per card E54153

The data presented in this document represents typical values for the production material.
 Typical values should not be used for specification limits.
 Please verify that any printed hard copy of this datasheet is current by referencing: www.rogerscorp.com/arlton

The information contained in this Data Sheet is intended to assist you in designing with Rogers' ARLON Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' ARLON Materials for each application. The Rogers logo, Helping power, protect, connect our world and ARLON are trademarks of Rogers Corporation or one of its subsidiaries. ©2017 Rogers Corporation, All rights reserved. Printed in U.S.A., 0217-PDF, Publication #202-049