

Bergamid™ AB700 UF grey VN8625CF

Polyamide 66/6 Copolymer

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Asia Pacific	• Europe
Features	• Flame Retardant	• Halogen Free	• Low (to None) Phosphorus Content
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.19 g/cm ³	1.19 g/cm ³	DIN 53479
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	479000 psi	3300 MPa	ISO 527-1/1
Tensile Stress (Break, 73°F (23°C))	10900 psi	75.0 MPa	ISO 527-2/5
Tensile Strain (Break, 73°F (23°C))	> 3.5 %	> 3.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.2 ft·lb/in ²	2.5 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	33 ft·lb/in ²	70 kJ/m ²	ISO 179/1eU
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	374 °F	190 °C	ISO 75-2/B
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	176 °F	80.0 °C	ISO 75-2/A
Maximum Use Temperature -- ³	176 °F	80 °C	IEC 60216
Short Time	356 °F	180 °C	
Melting Temperature (DSC)	469 °F	243 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+10 ohms	1.0E+10 ohms	IEC 60093
Volume Resistivity	1.0E+12 ohms·cm	1.0E+12 ohms·cm	IEC 60093
Relative Permittivity (1 MHz)	7.00	7.00	IEC 60250
Dissipation Factor (1 MHz)	0.30	0.30	IEC 60250
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			Internal Method
0.02 to 0.12 in (0.4 to 3.0 mm), ALL	V-0	V-0	
Glow Wire Ignition Temperature ⁴			IEC 60695-2-13
0.03 to 0.12 in (0.8 to 3.0 mm)	1760 °F	960 °C	

Copyright © 2023 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Notes

¹ Typical values are not to be construed as specifications.

² $\pm 0.03 \text{ g/cm}^3$

³ Continuous (GTP 50% Tensile)

⁴ 0.4 mm wire

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com