

CELSTRAN® +PP-GF45-05X551/1X | PP | Glass Reinforced

Description

Material code according to ISO 1043-1: PP

Polypropylene with 45 weight percent ash content, long glass fibers reinforced. The fibers are chemically coupled to the polypropylene matrix. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long. Concentrate for blending down on a fiber content of 20-30%

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Application field: Functional/structural parts for automotive


Physical properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ISO 1183

Mechanical properties	Value	Unit	Test Standard
Tensile modulus (1mm/min)	8800	MPa	ISO 527-2/1A
Tensile modulus (80°C)	6100	MPa	ISO 527-2/1A
Tensile strength (80°C)	80	MPa	ISO 527-2/1A
Tensile stress at break (5mm/min)	110	MPa	ISO 527-2/1A
Tensile strain at break (5mm/min)	2.1	%	ISO 527-2/1A
Elongation at break (80°C)	2.6	%	ISO 527-2/1A
Flexural modulus (23°C)	9000	MPa	ISO 178
Flexural modulus (80°C)	6000	MPa	ISO 178
Flexural strength (23°C)	170	MPa	ISO 178
Flexural strength (80°C)	90	MPa	ISO 178
Charpy impact strength @ 23°C	80.0	kJ/m ²	ISO 179/1eU
Charpy impact strength @ -30°C	82.0	kJ/m ²	ISO 179/1eU
Charpy notched impact strength @ 23°C	32.0	kJ/m ²	ISO 179/1eA
Charpy notched impact strength @ -30°C	30.0	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
Melting temperature (10°C/min)	166	°C	ISO 11357-1,-2,-3
DTUL @ 1.8 MPa	158	°C	ISO 75-1/-2
DTUL @ 8.0 MPa	138	°C	ISO 75-1/-2

CELSTRAN® +PP-GF45-05X551/1X | PP | Glass Reinforced

Typical injection moulding processing conditions



Pre Drying:

Necessary low maximum residual moisture content: 0.2%

It is normally not necessary to dry CELSTRAN PP. However, should there be surface moisture (condensate) on the molding compound as a result of incorrect storage, drying is required.

The product can then be stored in standard conditions until processed.

Temperature:

	T_{Manifold}	T_{Mold}	T_{Melt}	T_{Nozzle}	T_{Zone4}	T_{Zone3}	T_{Zone2}	T_{Zone1}	T_{Feed}
min (°C)	230	30	230	240	250	240	230	220	20
max (°C)	270	70	270	250	250	250	240	230	50

Pressure:

	Inj press	Hold press	Back pressure
min (bar)	600	400	0
max (bar)	1200	800	30

Speed:

Injection speed: slow

Screw speed

Screw diameter (mm)	16	25	40	55	75
Screw speed (RPM)	-	-	50	35	25

Special Info:

Assessment of mechanical values using an injection molding machine with dedicated screw. Implementation: Feb. 2010

Contact Information

Americas

8040 Dixie Highway, Florence, KY 41042 USA
 Product Information Service
 t: +1-800-833-4882 t: +1-859-372-3244
 Customer Service
 t: +1-800-526-4960 t: +1-859-372-3214
 e: info-engineeredmaterials-am@celanese.com

Asia

4560 Jinke Road, Zhang Jiang Hi Tech Park
 Shanghai 201203 PRC
 Customer Service
 t: +86 21 3861 9266 f: +86 21 3861 9599
 e: info-engineeredmaterials-asia@celanese.com

Europa

CELSTRAN® +PP-GF45-05X551/1X | PP | Glass Reinforced

Am Unisys-Park 1, 65843 Sulzbach, Germany
Product Information Service

t: +(00)-800-86427-531 t: +49-(0)-69-45009-1011
e: info-engineeredmaterials-eu@celanese.co

General Disclaimer

This publication was printed based on Celanese's present state of knowledge, and Celanese undertakes no obligation to update it. Because conditions of product use are outside Celanese's control, Celanese makes no warranties, express or implied, and assumes no liability in connection with any use of this information. Nothing herein is intended as a license to operate under or a recommendation to infringe any patents.

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.

Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.

Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards.

We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed (+49 (0) 69 30516299 for Europe, +1 859-372-3244 for the Americas and +86 21 3861 9266 for Asia) for additional technical information. Visit our web site for the appropriate Safety Data Sheets (SDS) before attempting to process our products. Feel free to call Customer Services for additional assistance.

The products mentioned herein are not intended for use in medical or dental implants.

© 2014 Celanese or its affiliates. All rights reserved. (Published 21.Dec.2015)

Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.