

Technical Data Sheet

Centrex ASA 821 1829 UVBLK



Acrylonitrile Styrene Acrylate

Product Description


Centrex ASA 821 is an injection molding grade with enhanced heat resistance and best chemical resistance among the ASA grades.

Regulatory Status

For regulatory compliance information, see ASA 821 1829 UVBLK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Injection Molding
Attribute	Good Chemical Resistance; Good Stiffness; UV Resistant
Forms	Pellets
Application	Household Goods; Housings

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	12	cm ³ /10 min	ISO 1133
Density	1.08	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (23 °C)	46.0	MPa	ISO 527-2
Nominal Tensile Strain at Break, (23 °C)	34	%	ISO 527-2
Tensile Strain at Yield, (23 °C)	2.3	%	ISO 527-2
Tensile Modulus	2360	MPa	ISO 527-1
Flexural Stress, (23 °C)	73.8	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C)	15	kJ/m ²	ISO 179
(-30 °C)	4.0	kJ/m ²	ISO 179
Hardness			
Rockwell Hardness, (R-Scale)	108		ISO 2039-2
Thermal			
Vicat Softening Temperature	109	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	97.1	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	85	°C	ISO 75-2/A



Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	240 to 280	°C
Mold Temperature	40 to 80	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.