

Technical Data Sheet

Centrex ASA 885A 90191 UVWHI



Acrylonitrile Styrene Acrylate

Product Description


Centrex ASA 885A 90191 UVWHI is a Acrylonitrile Styrene Acrylate material and is typically used in Coextrusion, Extrusion applications. Features include: Good Melt Strength, Good Weather Resistance, and Low Gloss.

Regulatory Status

For regulatory compliance information, see ASA 885A 90191 UVWHI [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Coextrusion; Extrusion
Attribute	Good Melt Strength; Good Weather Resistance; Low Gloss
Forms	Pellets
Application	Outdoor Applications; Profiles; Siding Substrate; Windows & Doors

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (220 °C/10.0 kg)	5.2	g/10 min	ASTM D1238
Density - Specific Gravity	1.12	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (5.1 mm/min)	23.0	MPa	ASTM D638
Tensile Strength at Break, (5.1 mm/min)	18.3	MPa	ASTM D638
Flexural Modulus, (1.3 mm/min, Tangent)	1160	MPa	ASTM D790
Flexural Strength, (1.3 mm/min)	37.2	MPa	ASTM D790
Impact			
Notched Izod Impact, (23 °C, 3.18 mm)	300	J/m	ASTM D256
Optical			
Gloss, (60°, 508 µm, Extruded Sheet)	3		ASTM D523



Extrusion Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Melt Temperature	177 to 204	°C
Suggested Max Moisture	<0.030	%
Die Temperature	177 to 191	°C
Suggested Max Regrind	40	%
Drying Temperature	82 to 93	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.