

Technical Data Sheet

Diamond ASA S225LG 32556 UVGRY



Acrylonitrile Styrene Acrylate

Product Description


Diamond ASA S225LG 32556 UVGRY is a Acrylonitrile Styrene Acrylate material and is typically used in Injection Molding applications. Features include: Good Weather Resistance, and Low Fogging.

Regulatory Status

For regulatory compliance information, see ASA S225LG 32556 UVGRY [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Injection Molding
Attribute	Good Weather Resistance; Low Fogging
Forms	Pellets

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (220 °C/10.0 kg)	11	g/10 min	ASTM D1238
Density - Specific Gravity	1.07	g/cm ³	ASTM D792
Mechanical			
Tensile Elongation at Yield, (51 mm/min, 23 °C, 3.18 mm, Injection Molded, Type I)	3.2	%	ASTM D638
Tensile Strength at Yield, (51 mm/min, 23 °C, 3.18 mm, Injection Molded, Type I)	42.7	MPa	ASTM D638
Tensile Strength at Break, (51 mm/min, 23 °C, 3.18 mm, Injection Molded, Type I)	37.9	MPa	ASTM D638
Tensile Elongation at Break, (51 mm/min, 23 °C, 3.18 mm, Injection Molded, Type I)	42	%	ASTM D638
Impact			
Notched Izod Impact, (23 °C, 3.18 mm, Injection Molded)	81	J/m	ASTM D256
Thermal			
Vicat Softening Temperature, (Loading 1 (10 N))	105	°C	ASTM D1525
Deflection Temperature Under Load Unannealed (264 psi), (3.18 mm, Injection Molded)	77.2	°C	ASTM D648



Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	80 to 85	°C
Suggested Max Moisture	0.02	%
Nozzle Temperature	220 to 260	°C
Processing (Melt) Temp	220 to 260	°C
Front Temperature	235 to 260	°C
Suggested Shot Size	40 to 70	%
Middle Temperature	232 to 260	°C
Rear Temperature	230 to 260	°C
Injection Rate	Fast	
Back Pressure	0.517 to 1.03	MPa
Mold Temperature	71 to 82	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.