

Technical Data Sheet

Diamond QR-2005-BK(RB)BLK

Acrylonitrile Butadiene Styrene



Product Description


Available with either high or low gloss.

Regulatory Status

For regulatory compliance information, see QR-2005-BK(RB)BLK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Developmental
Availability	North America
Processing Method	Injection Molding
Attribute	Good Impact Resistance
Forms	Pellets
Appearance	Colors Available; Natural Color

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/3.8 kg)	17	g/10 min	ASTM D1238
Density - Specific Gravity	1.06	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	45.9	MPa	ASTM D638
Flexural Strength at Yield	70.3	MPa	ASTM D790
Flexural Modulus	2490	MPa	ASTM D790
Impact			
Notched Izod Impact, (23 °C)	150	J/m	ASTM D256



Injection Parameters	Nominal Value	Units
----------------------	---------------	-------

Drying Time	2.0 to 4.0	hr
Drying Temperature	93	°C
Nozzle Temperature	>216	°C
Processing (Melt) Temp	216 to 260	°C
Front Temperature	216 to 238	°C
Middle Temperature	204 to 210	°C
Rear Temperature	188 to 210	°C
Mold Temperature	49 to 71	°C
Drying Time, Maximum	4	hr

Notes

These are typical property values not to be construed as specification limits. The typical values for this product may have been tested on a natural grade.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.