



Dow Corning® MB 50-011 Masterbatch

Dow Corning Corporation - Slip Agent / Lubricant / Mold Release / Processing Aid Masterbatch

Sunday, November 3, 2019

General Information

Product Description

Dow Corning® MB50-011 Masterbatch is a pelletized formulation containing 50% of an ultra-high molecular weight (UHMW) siloxane polymer dispersed in polyamide 6. It is designed to be used as an additive in most polyamide compatible systems to impart benefits such as processing improvements and modification of surface characteristics.

Liquid siloxane plastic additives have been used for several years to improve the lubricity and flow of thermoplastics. They are effective in this role although some difficulties have been experienced in the incorporation of liquids into thermoplastic melts without the use of specialized equipment. It has also been difficult to produce masterbatches with greater than 20% liquid siloxane because of processing difficulty and bleed problems.

The Dow Corning® MB Series Masterbatches address these problems by supplying a high concentration of an ultra-high molecular weight (UHMW) siloxane as a dispersion in a dry pellet form in a variety of thermoplastics.

APPLICATIONS

- Additive in polyamide compatible systems

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Agency Ratings	• FDA 21 CFR 177.1500	• FDA 21 CFR 177.1500(b)(6.1)	• FDA 21 CFR 181.28

ASTM & ISO Properties ¹

Additives General	Nominal Value	Unit
Additives Category	Masterbatch -- Slip Agent / Lubricant / Mold Release / Processing Aid -- Silicone-based	
Carrier Resin	Polyamide or copolymer (Nylon)	
Recommended for Use In	Polyamide or copolymer (Nylon)	
Forms	Pellets / Granules	
NFPA 704 Safety Rating		
1	Flammability	
0	•	Health
	•	Reactivity

Additives Physical	Nominal Value	Unit
Density	1.05	g/cm ³
Additive Concentration	50	%
State at Room Temperature	Solid	
Chemical Description	Siloxane	

Notes

¹ Typical properties: these are not to be construed as specifications.