

Technical Data Sheet

DuraGrip DGR-6150NCNAT



Thermoplastic Elastomer

Product Description


DuraGrip DGR 6150 is offered in an NC (colorable) version, and is designed to chemically bond to a wide variety of thermoplastic substrates including ABS, PC, Nylon 6, Nylon 6/6, glass filled Nylon, ASA, PC/ABS alloys, PBT, and PC/PBT alloys. It is easy to use in injection molding and extrusion processes. DGR 6150NC has excellent elastomeric properties and soft touch feel. *DuraGrip* bonding grades are hygroscopic, and for best results drying is recommended prior to use.

Regulatory Status

For regulatory compliance information, see DGR-6150NCNAT [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific; Europe; North America
Processing Method	Extrusion; Injection Molding
Attribute	Good Adhesion
Forms	Pellets

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.07	g/cm ³	ISO 1183
Density - Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Viscosity, (190 °C, 200 sec ⁻¹)	323	Pa·s	ASTM D3835
Mechanical			
Tensile Stress at 100%	1.8	MPa	ISO 37
Tensile Strength at Yield	8.07	MPa	ASTM D412
Tensile Stress at Yield	8.07	MPa	ISO 37
Tensile Strain at Break	540	%	ISO 37
Tensile Elongation at Break	540	%	ASTM D412
Hardness			
Shore Hardness, (Shore A, 5 sec)	52		ISO 868
Durometer Hardness, (Shore A, 5 sec)	52		ASTM D2240



Injection Parameters	Nominal Value	Units
Nozzle Temperature	227 to 249	°C
Screw Speed	50 to 150	rpm
Processing (Melt) Temp	227 to 254	°C
Front Temperature	227 to 238	°C
Middle Temperature	216 to 227	°C
Rear Temperature	204 to 221	°C
Mold Temperature	43 to 54	°C
Injection Pressure	2.76 to 5.52	MPa

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.