

Escorene™ Ultra AD 0433EH2

Ethylene Vinyl Acetate Copolymer Resin

Product Description

AD 0433EH2 is a copolymer of ethylene and vinyl acetate.

General

Additive	- Antiblock: No - Slip: No	- Thermal Stabilizer: Yes - Free Flowing Agent: Yes
Applications	Hot Melt Adhesives	
Form(s)	Pellets	

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.956 g/cm ³	0.956 g/cm ³	ExxonMobil Method
Melt Index ²	390 g/10 min	390 g/10 min	ExxonMobil Method
Vinyl Acetate Content	33.0 wt%	33.0 wt%	ExxonMobil Method
Peak Melting Temperature	138 °F	59 °C	ExxonMobil Method

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Modulus (0.20 in/min (5.0 mm/min))	910 psi	6.3 MPa	ASTM D638
Tensile Strength at Break 20 in/min (500 mm/min)	250 psi	1.7 MPa	ASTM D638
Elongation at Break (20 in/min (500 mm/min))	710 %	710 %	ASTM D638

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Molded properties were measured on 2 mm (78.7 mil) thick compression molded plaques prepared based on ASTM D 4703 Procedure C (Tensile ASTM D 638 : Type IV dumbbell).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Value reported is an estimate based on ExxonMobil's correlation from melt flow rate data measured at other standard conditions, based on ASTM D 1238.