

Escorene™ Ultra LD 705.MJ Blown

Ethylene Vinyl Acetate Copolymer Resin

Product Description

Escorene Ultra LD 705.MJ is a fractional melt index, 12.8 wt% vinyl acetate copolymer specialty film resin for applications requiring outstanding heat sealability, strength, and toughness.

General

Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Compounding ▪ Freezer Film ▪ Heat Seal Layer	▪ Liquid Packaging ▪ Primal Meat Bags ▪ Profile Extrusion	▪ Stretch Film

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.935 g/cm ³	0.935 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.40 g/10 min	0.40 g/10 min	ExxonMobil Method
Vinyl Acetate Content	12.8 wt%	12.8 wt%	ExxonMobil Method
Peak Melting Temperature	201 °F	94 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	167 °F	75 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	5100 psi	35 MPa	ASTM D882
Tensile Strength at Break TD	5100 psi	35 MPa	ASTM D882
Elongation at Break MD	350 %	350 %	ASTM D882
Elongation at Break TD	640 %	640 %	ASTM D882
Secant Modulus MD - 1% Secant	9900 psi	68 MPa	ASTM D882
Secant Modulus TD - 1% Secant	12000 psi	84 MPa	ASTM D882
Dart Drop Impact	750 g	750 g	ASTM D1709A
Elmendorf Tear Strength MD	80 g	80 g	ASTM D1922
Elmendorf Tear Strength TD	100 g	100 g	ASTM D1922

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	78	78	ASTM D2457
Haze	3.1 %	3.1 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (2 mil / 50.8 micron) made from LD 705.MJ on a 2.5 inch blown film line with a 6 inch die and 30 mil die gap at a 2.5:1 blow-up ratio and melt temperature of 360-380°F (182- 193°C).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.