

ExxonMobil™ HDPE HD 7845.30

High Density Polyethylene Resin

Product Description

ExxonMobil™ HD 7845.30 is a high density polyethylene resin that can be processed on high stalk, pocket extrusion or cast lines. Films made from HD 7845.30 resin exhibit an excellent stiffness balance. High thermal stability provides excellent film appearance and high quality recycle. HD 7845.30 resin is particularly recommended as a blend component with LLDPE for stiff clear films.

General

Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Blown Film ▪ Deli Wrap ▪ Food Packaging	▪ Heavy Duty Bags ▪ Oriented Film Products ▪ Overwrap Film	▪ Surface Protection Film
Form(s)	▪ Pellets		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.958 g/cm ³	0.958 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.45 g/10 min	0.45 g/10 min	ASTM D1238
High Load Melt Index (190°C/21.6 kg)	28 g/10 min	28 g/10 min	ASTM D1238
Peak Melting Temperature	270 °F	132 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	4800 psi	33 MPa	ASTM D882
Tensile Strength at Yield TD	5200 psi	36 MPa	ASTM D882
Tensile Strength at Break MD	11000 psi	70 MPa	ASTM D882
Tensile Strength at Break TD	5600 psi	39 MPa	ASTM D882
Elongation at Break MD	400 %	400 %	ASTM D882
Elongation at Break TD	6 %	6 %	ASTM D882
Secant Modulus MD - 1% Secant	150000 psi	1000 MPa	ASTM D882
Secant Modulus TD - 1% Secant	220000 psi	1500 MPa	ASTM D882
Dart Drop Impact	< 60 g	< 60 g	ASTM D1709A
Elmendorf Tear Strength MD	10 g	10 g	ASTM D1922
Elmendorf Tear Strength TD	1200 g	1200 g	ASTM D1922

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1.0 mil/25.4 micron) made from HD 7845.30 resin on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 405-425°F (207-218°C), a 60 mil (1.5 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.