

ExxonMobil™ PP8244E1

Polypropylene Impact Copolymer

Product Description

A high crystallinity, high impact copolymer resin designed for injection molded applications requiring excellent processing attributes.

General

Features	- Balanced Stiffness/Toughness - Good Impact Resistance	- Good Processability - Heat Aging Resistant	- Medium Molecular Weight - Nucleated
Appearance	Natural Color		
Form(s)	Pellets		
Processing Method	- Compounding - Injection Molding		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16 g/10 min	16 g/10 min	ISO 1133
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	2780 psi	19.2 MPa	ASTM D638
Elongation at Yield (2.0 in/min (51 mm/min))	7.0 %	7.0 %	ASTM D638
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min)	136000 psi	938 MPa	ASTM D790A
0.51 in/min (13 mm/min)	156000 psi	1080 MPa	ASTM D790B

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Instrumented Dart Impact			ASTM D3763
-40°F (-40°C), 0.125 in (3.18 mm)	34.2 ft·lb	46.4 J	
-20°F (-29°C), 0.125 in (3.18 mm)	29.3 ft·lb	39.7 J	
Notched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D256A

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	189 °F	87.0 °C	ASTM D648

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

This product is not intended for use in food contact application.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.