

GEON® Flex A7001

GEON Performance Solutions - Flexible Polyvinyl Chloride

Tuesday, June 18, 2024

General Information

Product Description

Interior compound used primarily in transparent applications. This product has been tested internally for for UL 94 HB specifications @ 3.0 and 1.5 mm. thickness and all colors. Listing can be acquired if needed

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• High Gloss	
Uses	• General Purpose		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.17	1.17	ASTM D792
Molding Shrinkage - Flow	0.019 to 0.023 in/in	1.9 to 2.3 %	ASTM D955
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Break)	1600 psi	11.0 MPa	ASTM D638
Tensile Elongation ² (Break)	400 %	400 %	ASTM D638
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tear Strength ³	230 lbf/in	40.3 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	18 %	18 %	ASTM D395
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A, Instant	70	70	
Shore A, 15 sec	61	61	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	-51.0 °F	-46.1 °C	ASTM D746
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Light Transmittance ⁴ (75.00 mil (1905 µm))	82.0 %	82.0 %	ASTM D1003
Haze (75.00 mil (1905 µm))	4.00 %	4.00 %	ASTM D1003

Processing Information

Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	380 to 400 °F	193 to 204 °C
Extrusion	Nominal Value (English)	Nominal Value (SI)
Melt Temperature	340 to 350 °F	171 to 177 °C

IMPORTANT: The information contained herein is believed to be accurate, but this information should not be construed as a product specification. It is offered for your consideration, investigation, testing, and verification. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Due to variations in methods, conditions, and equipment used commercially to process this product, no warranties or guarantees are made as to the suitability of this product for any particular application. Full-scale testing and end product performance are the responsibility of the user. GEON Performance Solutions is not liable for and the user assumes all risk and liability of any use or handling of this product. GEON PERFORMANCE SOLUTIONS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

GEON® Flex A7001

GEON Performance Solutions - Flexible Polyvinyl Chloride

Notes

¹ Typical properties: these are not to be construed as specifications.

² 20 in/min (510 mm/min)

³ Die C, 20 in/min (510 mm/min)

⁴ CIE Illuminant C

IMPORTANT: The information contained herein is believed to be accurate, but this information should not be construed as a product specification. It is offered for your consideration, investigation, testing, and verification. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Due to variations in methods, conditions, and equipment used commercially to process this product, no warranties or guarantees are made as to the suitability of this product for any particular application. Full-scale testing and end product performance are the responsibility of the user. GEON Performance Solutions is not liable for and the user assumes all risk and liability of any use or handling of this product. GEON PERFORMANCE SOLUTIONS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.