

Eltex® HD5240EA-B

High Density Polyethylene
INEOS Olefins & Polymers Europe

Technical Data

Product Description

Eltex® HD5240EA-B is a high-density polyethylene copolymer grade with a narrow molecular weight distribution, specially developed for injection of caps & closures applications requiring good environmental stress cracking resistance. Thanks to high purity and excellent organoleptic properties, this grade is particularly intended for the packaging in direct contact with beverages.

Typical applications

- Caps & closures for the packaging of still mineral water, functionalized beverages and slightly carbonated or pressurized beverages

Benefits and Features

- Easy processing
- Good environmental stress cracking resistance
- High impact strength
- Low warpage
- Slip agent free grade
- Excellent, quality controlled organoleptic properties. In order to preserve the excellent organoleptic properties, it is important not to exceed a melt temperature of 250°C during processing.

General

Material Status	• Commercial: Active		
Literature ¹	• Technical Datasheet (English)		
Search for UL Yellow Card	• INEOS Olefins & Polymers Europe		
Availability	• Europe		
Features	• Copolymer • Food Contact Acceptable • Good Organoleptic Properties	• Good Processability • High ESCR (Stress Crack Resist.) • High Impact Resistance	• High Purity • Low Warpage • Narrow Molecular Weight Distribution
Uses	• Caps	• Closures	
RoHS Compliance	• Contact Manufacturer		
Processing Method	• Injection Molding		

Physical	Nominal Value Unit	Test Method
Density	0.950 g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0 g/10 min	ISO 1133
Environmental Stress-Cracking Resistance	13.0 hr	Internal Method
Mechanical	Nominal Value Unit	Test Method
Tensile Modulus	1100 MPa	ISO 527-2/1B
Tensile Stress (Yield)	25.0 MPa	ISO 527-2/1B
Impact	Nominal Value Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	5.5 kJ/m²	ISO 179

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.