

ExxonMobil™ HDPE HD 6605.70

High Density Polyethylene Copolymer Resin

Product Description

HD 6605.70 is a narrow molecular weight hexene copolymer designed for a wide range of injection molding applications, offering excellent ESCR with good stiffness-toughness balance. Ideally suited for articles requiring rugged physical performance in cold temperature environments.

General

Availability ¹	• Latin America	• North America	• South America
Additive	• Anti-gas fading: Yes		
Applications	• Automotive Components • Industrial Closures	• Recreational Vehicle - Components • Waste Carts	
Revision Date	• March 2013		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.948 g/cm ³	0.948 g/cm ³	ASTM D4883
Melt Index (190°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	156 °F	69 °C	ASTM D648
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	108 °F	42 °C	ASTM D648B
Peak Melting Temperature	266 °F	130 °C	ASTM D3418

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	3400 psi	23 MPa	ASTM D638
Flexural Modulus			ASTM D790B
1% Secant	160000 psi	1100 MPa	
2% Secant	140000 psi	970 MPa	
Environmental Stress-Crack Resistance			ASTM D1693B
10% Igepal, F50	20 hr	20 hr	

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (-40°F (-40°C))	1.0 ft-lb/in	55 J/m	ASTM D256

Additional Information

- Properties are based on compression molded samples.
- Test procedures may be modified to accommodate operating conditions or facility limitations.
- Tensile Strength at Yield and Elongation at Break tested using ASTM D638 Type IV, 50 mm/min.

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.