

Technical Data Sheet

Hifax EYG 382P T1 C12716



Polypropylene Compounds

Product Description

Hifax EYG 382P T1 C12716 is a 28% glass fiber reinforced PP copolymer, with high melt flow rate, high stiffness, and good UV resistance. The product is available as a customized color matched, pellet form. This grade is delivered in C12716 color version.

Regulatory Status

For regulatory compliance information, see Hifax EYG 382P T1 C12716 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Asia-Pacific
Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Excellent Stiffness; Good UV Resistance; High Flow; Pleasing Surface Appearance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	26	g/10 min	ISO 1133-1
Density, (23 °C)	1.12	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	5750	MPa	ISO 178
Flexural Stress, (3.5% Strain)	105	MPa	ISO 178
Tensile Stress at Yield	72	MPa	ISO 527-1, -2
Tensile Strain at Break	4.5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	12	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	143	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.