

Technical Data Sheet

Hifax TYC520P BLACK



Polypropylene Compounds

Product Description

Hifax TYC 520P Black is a high flow, high impact copolymer polypropylene especially designed for injection moulding large, thin wall parts. This grade has good dimensional stability, painting ability and UV stability. This grade can be used for automotive exterior parts, such as bumper. This grade is black, pellet form.

Regulatory Status

For regulatory compliance information, see Hifax TYC520P BLACK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Asia-Pacific
Application	Automotive Parts; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; Good UV Resistance; High Flow; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	33	g/10 min	ASTM D1238
Density, (23 °C)	0.965	g/cm ³	ASTM D792
Mechanical			
Flexural Modulus, (23 °C)	1560	MPa	ASTM D790
Tensile Stress at Yield, (23 °C)	19	MPa	ASTM D638
Impact			
Notched Izod Impact Strength			
(23 °C)	650	J/m	ASTM D256
(-30 °C)	70	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.