

Technical Data Sheet

HP423MX02



Polypropylene, Homopolymer

Product Description

HP423MX02 is a polypropylene homopolymer available in pellet form. This resin is typically used in cast film applications. It is formulated with slip additive.

Regulatory Status

For regulatory compliance information, see HP423MX02 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). To obtain copies of these documents, please contact your LyondellBasell product safety representative.

Status	Developmental
Availability	North America
Application	Clarity Film; Foamed Sheet; Food Packaging Film; Lamination Film; Nonwovens
Market	Flexible Packaging
Processing Method	Cast Film; Extrusion Flat-die; Staple Fiber
Attribute	Good Optical Properties; High Clarity; High Gloss; High Slip; Low Coefficient of Friction

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	8.5	g/10 min	8.5	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	204000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1407	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4860	psi			ASTM D638
(50 mm/min)			34	MPa	ASTM D638
Tensile Elongation at Yield	12	%	12	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.6	ft-lb/in			ASTM D256
(23 °C, Method A)			32	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	216	°F			ASTM D648
(0.45 MPa, Unannealed)			102	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.