

ICORENE® 1061 ESF WHITE 1001

Linear Low Density Polyethylene
Rotomolding

Product Description

ICORENE® 1061 ESF WHITE 1001 is the "next generation" enhanced surface finish polyethylene, specifically developed for rotational moulding.

This grade is designed to remove the surface pinholes during processing for applications such as hygienic, medical, furniture and design applications. ICORENE® 1061 ESF WHITE 1001 is easy to process, has a good flow and good physical properties.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Additive	• UV Stabilizer		
Features	• General Purpose • Good Flow	• Good Moldability • Good Processability	• Good Stiffness • UV Resistant
Uses	• Food Containers • Furniture	• General Purpose • Hygiene	• Toys
Appearance	• White		
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.934 g/cm ³	0.934 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2610 psi	18.0 MPa	ASTM D638
Tensile Elongation (Yield)	23 %	23 %	ASTM D638
Flexural Modulus	79800 psi	550 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹ (-4°F (-20°C))	3.82 in·lb/mil	170 J/cm	Internal Method
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	57	57	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Melting Temperature (DSC)	257 °F	125 °C	ISO 3146

Notes

¹ Based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2019

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

ICORENE[®] 1061 ESF WHITE 1001

Linear Low Density Polyethylene
Rotomolding

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.