

Technical Data Sheet

Icorene 1505 BLK 9001



Polyethylene, Crosslinked

Product Description

Icorene 1505 Black 9001 is a crosslinkable black high density polyethylene specifically developed for rotational moulding. This grade is particularly suitable for use in applications requiring exceptional impact resistance at low temperature, toughness and excellent ESCR such as fuel tanks. The original cross linking system used is low odor and allows a perfect moulding of the part free of pinholes. *Icorene* 1505 Black 9001 is TÜV approved, protocolnr 163XS0034-00.

Regulatory Status

For regulatory compliance information, see *Icorene* 1505 BLK 9001 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Processing Method	Rotomolding
Attribute	Crosslinkable; Good Processability; High ESCR (Environmental Stress Cracking Resistance); High Impact Resistance; UV Resistant
Forms	Powder
Appearance	Black
Additive	UV Stabilizer
Application	Industrial Containers

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	0.943	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Yield	21	MPa	ASTM D638
Environmental Stress Crack Resistance			
(10% Igepal, 50 °C)	>1000	hr	ASTM D1693
(Rotational Molded, F50, 100% AntaroX, 50 °C)	>1000	hr	ASTM D1693
Flexural Modulus	700	MPa	ASTM D790
Tensile Elongation at Break	600	%	ASTM D638
Impact			
Drop Impact Resistance, (-40 °C, 3.20 mm)	320	J/cm	ARM
Thermal			
Vicat Softening Temperature, (A (10N), 50 °C/h)	127	°C	ISO 306
Deflection Temperature Under Load Unannealed (1.80 MPa)	43.0	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.