

Technical Data Sheet

Icorene 1614-3442G BLACK



Polyethylene, Linear Medium Density

Product Description

Icorene 1614 is a hexene linear medium density polyethylene specifically developed for use in rotational molding. This grade is designed for applications requiring good processability, stiffness and toughness. This product is particularly suitable for the production of diesel fuel tanks. *Icorene* 1614 is TUV ECE R34 approved, protocol no: 185XS0148-00.

Regulatory Status

For regulatory compliance information, see *Icorene* 1614-3442G BLACK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Rotomolding
Attribute	Good ESCR (Environmental Stress Cracking Resistance); Good Processability; Good Stiffness; Good Toughness; UV Resistant
Forms	Powder
Appearance	Black
Additive	UV Stabilizer
Application	Agricultural Tanks; Heavy Transportation; Lawn & Garden Equipment; Outdoor Applications

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	3.5	g/10 min	ASTM D1238
Density	0.939	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Yield	19.9	MPa	ASTM D638
Environmental Stress Crack Resistance			
(F50, 10% Igepal, 50 °C)	60.0	hr	ASTM D1693
(F50, 100% Igepal, 50 °C)	>1000	hr	ASTM D1693
Flexural Modulus, (1% Secant)	833	MPa	ASTM D790
Tensile Elongation at Break	240	%	ASTM D638
Impact			
Impact Strength			
(-40 °C, 3.18 mm, Rotational Molded)	75	J	ARM
(-40 °C, 6.35 mm, Rotational Molded)	>258	J	ARM
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa), (Rotational Molded)	60.0	°C	ASTM D648
Deflection Temperature Under Load Unannealed (1.80 MPa)	38.8	°C	ASTM D648
Peak Melting Temperature	126	°C	ASTM D3418

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.