

ICORENE® 1741 Black 9001

High Density Polyethylene
Rotomolding

Product Description

ICORENE® 1741 BLACK 9001 is a metallocene high density polyethylene specifically developed for use in rotational moulding.

This grade is designed for use in many different rotomoulding applications. It has good overall mouldability, high rigidity and very good toughness.

General

Material Status	• Commercial: Active
Availability	• Europe
Additive	• UV Stabilizer
Features	• Good Impact Resistance • Good Toughness • Good Moldability • High Rigidity • UV Resistant
Uses	• Tanks • Thick-walled Parts
Appearance	• Black
Forms	• Powder
Processing Method	• Rotational Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.940 g/cm ³	0.940 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2900 psi	20.0 MPa	ISO 527-2
Tensile Elongation (Break)	800 %	800 %	ISO 527-2
Flexural Modulus	116000 psi	800 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance (-4°F (-20°C))	4.05 in·lb/mil	180 J/cm	ISO 6603-2
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	149 °F	65.0 °C	ISO 75-2/B
Melting Temperature	259 °F	126 °C	ISO 11357

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2019

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.