

## Technical Data Sheet

### *Icorene* 1761 ORE 3218



Polyethylene, Linear Low Density, Metallocene

#### Product Description

*Icorene* 1761 is a metallocene linear low density polyethylene for rotational moulding applications. This grade is suitable for use in general purpose applications. It has a good balance of properties such as toughness, easy flow, high impact, and surface gloss.

#### Regulatory Status

For regulatory compliance information, see *Icorene* 1761 ORE 3218 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

|                   |                                                                             |
|-------------------|-----------------------------------------------------------------------------|
| Status            | Commercial: Active                                                          |
| Availability      | Europe                                                                      |
| Processing Method | Rotomolding                                                                 |
| Attribute         | Good Toughness; High Flow; High Gloss; High Impact Resistance; UV Resistant |
| Forms             | Powder                                                                      |
| Appearance        | Natural Color; Unspecified Color                                            |
| Additive          | UV Stabilizer                                                               |
| Application       | General Purpose; Molds/Dies/Tools                                           |

| Typical Properties                                | Nominal Value | Units             | Test Method |
|---------------------------------------------------|---------------|-------------------|-------------|
| <b>Physical</b>                                   |               |                   |             |
| Melt Flow Rate, (190 °C/2.16 kg)                  | 6.0           | g/10 min          | ASTM D1238  |
| Density                                           | 0.935         | g/cm <sup>3</sup> | ASTM D1505  |
| <b>Mechanical</b>                                 |               |                   |             |
| Tensile Strength at Yield                         | 18.0          | MPa               | ISO 527-2   |
| Tensile Strength at Break                         | 11.0          | MPa               | ISO 527-2   |
| Environmental Stress Crack Resistance             |               |                   |             |
| (10% Igepal)                                      | >300          | hr                | ASTM D1693  |
| (100% Igepal)                                     | >1000         | hr                | ASTM D1693  |
| Flexural Modulus                                  | 700           | MPa               | ISO 178     |
| Tensile Elongation at Break                       | >800          | %                 | ASTM D638   |
| <b>Impact</b>                                     |               |                   |             |
| Drop Impact Resistance, (-20 °C, Internal Method) | 190           | J/cm              | ASTM D4226  |
| <b>Thermal</b>                                    |               |                   |             |
| Vicat Softening Temperature                       | 121           | °C                | ISO 306     |
| Melting Temperature                               | 123           | °C                | ISO 11357   |

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.