

ICORENE® 7620 Fuel Lock

Polyamide 6
Rotomolding

Product Description

ICORENE® 7620 Fuel Lock is a high impact Polyamide 6 specifically developed for the rotational moulding of fuel tanks.

This grade has been developed in collaboration with DSM and once moulded the ICORENE® 7620 Fuel Lock has higher resistance through fuel evaporation.

Thus, monolayer tanks of this grade with thin wall thickness can easily pass the permeation requirements of the Environmental Protection Agency (EPA, USA) for CE10.

General

Material Status	• Commercial: Active
Availability	• Europe
Features	• Fuel Resistant • Gas Barrier • High Heat Resistance
Uses	• Fuel Tanks
Appearance	• Black • Natural Color
Forms	• Powder
Processing Method	• Rotational Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ASTM D1505
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Flexural Modulus	261000 psi	1800 MPa	ISO 178/A
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹ (32°F (0°C))	> 5.62 in·lb/mil	> 250 J/cm	Internal Method
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	167 °F	75.0 °C	ISO 75-2/B
Melting Temperature	428 °F	220 °C	ISO 11357-3

Notes

¹ condition 1 hours in water at 70°C for a part of 3mm thickness.
Based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2019

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.