

Technical Data Sheet

Icorene 9402 NATURAL 0000



Thermoplastic Elastomer

Product Description

Icorene 9402 is a thermoplastic elastomer specifically developed for rotational moulding in collaboration with API Spa. This grade offers optimum cold and hot elasticity with UV resistance. It has an excellent appearance with excellent soft touch properties. *Icorene* 9402 is a tough material which will not break @ -40°C impact strength.

Regulatory Status

For regulatory compliance information, see *Icorene* 9402 NATURAL 0000 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Processing Method	Rotomolding
Attribute	High Elasticity; Soft; UV Resistant
Forms	Powder
Appearance	Natural Color; Unspecified Color
Additive	UV Stabilizer
Application	Furniture; High Temperature Applications; Outdoor Furnishings

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (220 °C/2.16 kg)	30	g/10 min	ISO 1133
Density	0.89	g/cm ³	ISO 1183
Mechanical			
Tensile Elongation at Yield	30	%	ASTM D638
Tensile Strength at Break	>8.00	MPa	ASTM D638
Tensile Strain at Break	>2000	%	ASTM D638
Flexural Modulus	100	MPa	ASTM D790
Hardness			
Durometer Hardness, (Shore A)	74		ASTM D2240

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.