

ICORENE® K 4140

Crosslinked Polyethylene
Rotomolding

General			
Material Status	• Commercial: Active		
Availability	• Latin America		
Additive	• UV Stabilizer		
Features	• Abrasion Resistant • Copolymer • Crosslinkable	• Good Impact Resistance • High Rigidity • Octene Comonomer	• UV Resistant
Appearance	• Natural Color		
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.941 g/cm ³	0.941 g/cm ³	ASTM D1505
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	2970 psi	20.5 MPa	ASTM D638
Tensile Elongation ¹ (Break)	950 %	950 %	ASTM D638
Flexural Modulus ²	110000 psi	760 MPa	ASTM D790
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Accelerated Aging	5.5 month	5.5 month	ASTM G26

Notes

¹ 2.0 in/min (50 mm/min)

² 0.051 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2019

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.