

Technical Data Sheet

Icorene N1008-1200 NAT0000XX



Ethylene Vinyl Acetate

Product Description

Icorene N1008 is a premium copolymer of ethylene vinyl acetate specifically designed for the preparation of masterbatch. The powder form can achieve better colour developments or additive dispersion in a masterbatch than the pellet form. The vinyl acetate content is about 9%. This grade has a maximum processing temperature of 270°C.

Regulatory Status

For regulatory compliance information, see *Icorene* N1008-1200 NAT0000XX [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Attribute	Copolymer; Dispersible; Food Contact Acceptable; Good Colorability; Heat Stabilized
Forms	Powder
Additive	Heat Stabilizer
Application	Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	9.0	g/10 min	ASTM D1238
Density, (Internal Method)	0.929	g/cm ³	ASTM D1505
Vinyl Acetate Content, (Internal Method)	9.0	wt %	
Mechanical			
Tensile Elongation at Break	>100	%	ASTM D638
Tensile Modulus	74	MPa	ASTM D638
Hardness			
Durometer Hardness, (Shore A)	93		ASTM D2240
Thermal			
Vicat Softening Temperature	72	°C	ASTM D1525
Peak Melting Temperature	96	°C	ASTM D3418



Injection Parameters	Nominal Value	Units
Processing (Melt) Temp	<270	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.