

Technical Data Sheet

Icorene N2102-1000 NAT



Low Density Polyethylene

Product Description

Icorene N2102 is a low density polyethylene resin designed for injection moulding, compound and masterbatch applications. This grade is characterized by good toughness, stiffness and processability.

Regulatory Status

For regulatory compliance information, see *Icorene* N2102-1000 NAT [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Processing Method	Compounding
Attribute	Good Processability; Good Stiffness; Good Toughness
Forms	Powder
Application	General Purpose; Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	7.5	g/10 min	ASTM D1238
Density	0.919	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Yield	10	MPa	ASTM D638
Tensile Elongation at Break	500	%	ASTM D638
Hardness			
Durometer Hardness, (Shore D)	46		ASTM D2240
Thermal			
Vicat Softening Temperature	87	°C	ASTM D1525
Peak Melting Temperature	106	°C	ASTM D3418

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.