

Technical Data Sheet

Icorene N2170-700 NAT0000XX



Low Density Polyethylene

Product Description

Icorene N2170 is a low density polyethylene resin with an excellent fluidity. It can be successfully added to low flowing LDPE grades to improve their processability. This grade is also used for compound and masterbatch applications.

Regulatory Status

For regulatory compliance information, see *Icorene* N2170-700 NAT0000XX [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific; Europe
Processing Method	Compounding
Attribute	Good Processability; High Flow
Forms	Powder
Application	Blending; Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	70	g/10 min	ASTM D1238
Density	0.916	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Break	7	MPa	ASTM D638
Flexural Modulus	150	MPa	ASTM D790
Hardness			
Durometer Hardness, (Shore D)	40		ASTM D2240
Thermal			
Vicat Softening Temperature	77	°C	ASTM D1525
Peak Melting Temperature	102	°C	ASTM D3418

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.