

Technical Data Sheet

Icorene N2308-1000 NATXX



Linear Low Density Polyethylene

Product Description

Icorene N2308 is a linear low density polyethylene produced by slurry loop low pressure process with hexene as co-monomer. This grade contains antioxidant stabilizers and has excellent mechanical properties and can be used alone, or blended or co-extruded in a wide variety of blown film applications.

Regulatory Status

For regulatory compliance information, see *Icorene* N2308-1000 NATXX [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Processing Method	Cast Film
Attribute	Good Processability
Forms	Powder
Additive	Antioxidant
Application	Blown Film; Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	0.15	g/10 min	ASTM D1238
Density	0.934	g/cm ³	ASTM D1505
Mechanical			
Tensile Stress at Yield, (0.0200 mm)	19.0	MPa	ISO 527-3
Tensile Strain at Break, (0.0200 mm)	500	%	ISO 527-3
Flexural Modulus	620	MPa	ISO 178
Tensile Stress at Break, (0.0200 mm)	52.0	MPa	ISO 527-3
Thermal			
Peak Melting Temperature	125	°C	ASTM D3418

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.