

Technical Data Sheet

Icorene N4425-2000 NAT 0000



Polypropylene, Homopolymer

Product Description

Icorene N4425 is a polypropylene homopolymer with a high fluidity. This grade is suitable for injection moulding and its main applications are thin walled packaging items or housewares.

Regulatory Status

For regulatory compliance information, see *Icorene* N4425-2000 NAT 0000 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Processing Method	Compounding
Attribute	High Flow; Homopolymer
Forms	Powder
Application	Masterbatch; Thin-walled Packaging

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mechanical			
Tensile Elongation at Yield	10	%	ASTM D638
Tensile Strength at Yield	30	MPa	ASTM D638
Flexural Modulus	1250	MPa	ASTM D790
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m ²	ISO 179
Hardness			
Durometer Hardness, (Shore D)	69		ASTM D2240
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa)	95	°C	ISO 75-2/B

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.