

Technical Data Sheet

Icorene N7130 GRY 7781



Polyethylene, Unspecified

Product Description

Icorene N7130 is a polyethylene based coating powder designed for encapsulating wire goods. Compared with standard powders, this grade will have improved flow behaviour, process faster and enable users to make savings through thinner coatings achieved at lower oven temperatures. This grade is used for fluidized bed coating applications by manual dip coating.

Regulatory Status

For regulatory compliance information, see *Icorene* N7130 GRY 7781 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Attribute	Good Abrasion Resistance; Good Flow; Good Processability
Forms	Powder
Appearance	Unspecified Color
Application	Coating Applications; Industrial Applications; Wire & Cable

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	0.924	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Yield	8	MPa	ASTM D638
Tensile Elongation at Break	>500	%	ASTM D638
Impact			
Ductile/Brittle Transition Temperature	-70	°C	ASTM D746
Hardness			
Durometer Hardness, (Shore D)	49		ASTM D2240
Thermal			
Peak Melting Temperature	118	°C	ASTM D3418

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.