

Technical Data Sheet

Icorene N9602-1200 NAT0000XX



Polyamide 6

Product Description

Icorene N9602 is a polyamide 6 grade with an easy release and a rapid solidification. This grade is used for masterbatch applications.

Regulatory Status

For regulatory compliance information, see *Icorene* N9602-1200 NAT0000XX [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Processing Method	Injection Molding
Attribute	Good Flow; Good Mold Release
Forms	Powder
Application	General Purpose; Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.14	g/cm ³	ISO 1183
Viscosity Number, (96% H ₂ SO ₄ (Sulphuric Acid))	2.70	cm ³ /g	ISO 307
Mechanical			
Tensile Elongation at Yield	20	%	ASTM D638
Tensile Strength at Yield	80	MPa	ASTM D638
Flexural Modulus	2700	MPa	ASTM D790
Tensile Elongation at Break	75	%	ASTM D638
Impact			
Charpy Impact Strength - Notched, (23 °C)	20	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature	213	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	175	°C	ISO 75-2/B
DSC Melting Point	222	°C	ISO 3146

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.