

INEOS HDPE J50-200-178

High Density Polyethylene
INEOS Olefins & Polymers USA

Technical Data

Product Description

J50-200-178 is a high density polyethylene copolymer intended for the injection molding of closures for beverages. Because of its high purity and excellent organoleptic properties, this grade is certified as low taste and is intended for packaging in direct contact with beverages. This material meets the Food and Drug Administration requirements of 21CFR 177.1520.

Typical Applications

- Caps and closures for the packaging of carbonated beverages and water
- Injection molded applications where low taste and odor are critical.

General

Material Status	• Commercial: Active		
Literature ¹	• Processing - Injection Molding (English) • Technical Datasheet (English)		
Search for UL Yellow Card	• INEOS Olefins & Polymers USA		
Availability	• North America		
Features	• Copolymer	• Good Organoleptic Properties	• Low to No Odor
	• Food Contact Acceptable	• High Purity	• Low to No Taste
Uses	• Caps	• Closures	
Agency Ratings	• FDA 21 CFR 177.1520		
RoHS Compliance	• Contact Manufacturer		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value Unit	Test Method
Density	0.952 g/cm ³	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance 100% Igepal	14.0 hr	ASTM D1693B

Mechanical	Nominal Value Unit	Test Method
Tensile Strength ³ (Yield)	27.6 MPa	ASTM D638
Tensile Elongation ³ (Break)	> 1000 %	ASTM D638
Flexural Modulus - Tangent	1210 MPa	ASTM D790

Impact	Nominal Value Unit	Test Method
Notched Izod Impact	120 J/m	ASTM D256

Hardness	Nominal Value Unit	Test Method
Durometer Hardness (Shore D)	65	ASTM D2240

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed	77.0 °C	ASTM D648
Brittleness Temperature	< -75.0 °C	ASTM D746
Vicat Softening Temperature	131 °C	ASTM D1525

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ 51 mm/min