

Technical Data Sheet

Invision GX 5080G2F-881559 LT DOVE



Thermoplastic Elastomer

Product Description

TPE Styrenic Rubber

Regulatory Status

For regulatory compliance information, see *Invision* GX 5080G2F-881559 LT DOVE [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status Commercial: Active

Availability North America

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	0.95	g/cm ³	ISO 1183
Melt Viscosity, (200 °C, 243 sec ⁻¹)	180	Pa·s	ASTM D3835
Mechanical			
Tensile Stress, (100%, 500 mm/min)	7.20	MPa	ISO 527-2
Tear Strength, (500 mm/min)	23.0	kN/m	ISO 34-1
Hardness			
Shore Hardness, (Shore A, 15 sec)	82		ISO 868

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.