

Akulon® K224-PG6

Property Data

(PA6+Imod)-GF30

30% Glass Reinforced, Impact Modified

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES		dry / cond	
Molding shrinkage (parallel)	0.25 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
MECHANICAL PROPERTIES		dry / cond	
Tensile modulus	8500 / 5500	MPa	ISO 527-1/-2
Stress at break	145 / 100	MPa	ISO 527-1/-2
Strain at break	4.5 / 9	%	ISO 527-1/-2
Charpy impact strength (+23°C)	95 / 110	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	100 / 100	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	25 / 45	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	17 / 17	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		dry / cond	
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.9 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES		dry / cond	
Relative permittivity (100Hz)	3.8 / 14	-	IEC 60250
Relative permittivity (1 MHz)	3.5 / 4.5	-	IEC 60250
Dissipation factor (100 Hz)	90 / 3000	E-4	IEC 60250
Dissipation factor (1 MHz)	150 / 1200	E-4	IEC 60250
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 60093
Surface resistivity	* / 1E14	Ohm	IEC 60093
Electric strength	25 / 20	kV/mm	IEC 60243-1
Comparative tracking index	* / 600	-	IEC 60112
OTHER PROPERTIES		dry / cond	
Water absorption	5.7 / *	%	Sim. to ISO 62
Humidity absorption	1.7 / *	%	Sim. to ISO 62
Density	1320 / -	kg/m ³	ISO 1183

05.07.2006

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information.