

Technical Data Sheet

Alathon L5040

High Density Polyethylene



Product Description

Alathon L5040 is able to incorporate high levels of post-consumer recycle and retain excellent bottle physical properties. This resin provides high ESCR and processing stability. Typical applications include stress crack resistant bottles and extruded pipe and conduit.

Regulatory Status

For regulatory compliance information, see *Alathon* L5040 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Bottles for Industrial Use
Market	Rigid Packaging
Processing Method	Extrusion Blow Molding
Attribute	High ESCR (Environmental Stress Cracking Resistance)

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.40	g/10 min	0.40	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm ³	0.949	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (1% Secant)	160000	psi	1100	MPa	ASTM D790
Tensile Strength at Yield	3400	psi	23.4	MPa	ASTM D638
Tensile Elongation at Break	>600	%	>600	%	ASTM D638
Environmental Stress Crack Resistance, F ₅₀ (100% Igepal®, Cond B)	>1000	hr	>1000	hr	ASTM D1693
Impact					
Tensile Impact Strength	188	ft-lb/in ²	395	kJ/m ²	ASTM D1822
Hardness					
Shore Hardness, (Shore D)	63		63		ASTM D2240
Thermal					
Vicat Softening Temperature	262	°F	128	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-103	°F	<-75	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	169	°F	76	°C	ASTM D648

Notes

Igepal® is a registered trademark of Rhodia.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.