

Formolene® LH5320

High Density Polyethylene
Formosa Plastics Corporation, U.S.A.

Technical Data

Product Description

Formolene® LH5320 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

General

Material Status	• Commercial: Active		
Literature ¹	• Technical Datasheet (English)		
Search for UL Yellow Card	• Formosa Plastics Corporation, U.S.A. • Formolene®		
Availability	• North America		
Features	• Food Contact Acceptable	• High Density	
Uses	• Food Containers	• Household Goods	• Toys
Agency Ratings	• EC 1907/2006 (REACH)	• FDA 21 CFR 177.1520	
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value Unit	Test Method
Density	0.953 g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20 g/10 min	ASTM D1238
Mechanical	Nominal Value Unit	Test Method
Tensile Strength (Yield)	27.1 MPa	ASTM D638
Flexural Modulus	903 MPa	ASTM D790

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.