

LNP* Thermocomp* RB00A

Polyamide 66

SABIC Innovative Plastics Europe



IDES | Prospector

ides.com/prospector

Technical Data

Product Description

50% glass beads filled Polyamide 66 injection moulding resin.

Also known as: LNP* Thermocomp* Compound RB10010
Product reorder name: RB00A

General

Material Status	• Commercial: Active
Literature ¹	• Technical Datasheet
Search for UL Yellow Card	• SABIC Innovative Plastics Europe • LNP* Thermocomp*
Availability	• Europe
Filler / Reinforcement	• Glass Bead, 50% Filler by Weight
RoHS Compliance	• RoHS Compliant
Processing Method	• Injection Molding

Physical	Nominal Value Unit	Test Method
Density	1.56 g/cm ³	ISO 1183
Molding Shrinkage - Flow ³	0.50 to 0.80 %	Internal Method
Water Absorption (Saturation, 23°C)	4.5 %	ISO 62

Mechanical	Nominal Value Unit	Test Method
Tensile Modulus	6200 MPa	ISO 527-2/1
Tensile Stress (Break)	85.0 MPa	ISO 527-2/5
Tensile Strain (Break)	2.5 %	ISO 527-2/5
Flexural Modulus ⁴	6000 MPa	ISO 178
Flexural Strength ^{4, 5}	140 MPa	ISO 178

Impact	Nominal Value Unit	Test Method
Charpy Unnotched Impact Strength ⁶ (23°C)	30 kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength ⁷		ISO 180/1A
-40°C	3.0 kJ/m ²	
-20°C	4.0 kJ/m ²	
23°C	5.0 kJ/m ²	

Thermal	Nominal Value Unit	Test Method
Heat Deflection Temperature ⁸		
0.45 MPa, Unannealed, 100 mm Span	245 °C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	175 °C	ISO 75-2/Ae
Vicat Softening Temperature	255 °C	ISO 306/A50
CLTE		ISO 11359-2
Flow: 23 to 60°C	0.000030 cm/cm/°C	
Transverse: 23 to 60°C	0.000030 cm/cm/°C	

Electrical	Nominal Value Unit	Test Method
Comparative Tracking Index		IEC 60112
--	500 V	
Solution B	400 V	

Flammability	Nominal Value Unit	Test Method
Flame Rating (1.60 mm, Testing by SABIC)	HB	UL 94

Injection	Nominal Value Unit
Drying Temperature	75.0 to 85.0 °C
Drying Time	4.0 to 6.0 hr
Suggested Max Moisture	0.20 %

LNP* Thermocomp* RB00A

Polyamide 66

SABIC Innovative Plastics Europe



ides.com/prospector

Injection	Nominal Value Unit
Hopper Temperature	60.0 to 80.0 °C
Rear Temperature	270 to 290 °C
Middle Temperature	260 to 280 °C
Front Temperature	260 to 280 °C
Nozzle Temperature	250 to 270 °C
Processing (Melt) Temp	260 to 290 °C
Mold Temperature	70.0 to 120 °C

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ Tensile Bar

⁴ 2.0 mm/min

⁵ Break

⁶ 80*10*4 sp=62mm

⁷ 80*10*4

⁸ 120*10*4 mm

LNP* Thermocomp* RB00A

Polyamide 66

SABIC Innovative Plastics Europe



ides.com/prospector

Where to Buy

Supplier

SABIC Innovative Plastics Europe

, Netherlands

Telephone: +36-1-238-5060

Web: <http://www.sabic-ip.com/>

Distributor

Polymix

Telephone: +33-3-8920-1380

Web: <http://www.polymix.eu/>

Availability: France

RESINEX Group

RESINEX is a Pan European distribution company. Contact RESINEX for availability of individual products by country.

Telephone: +32-14-672511

Web: <http://www.resinex.com/>

Availability: Europe

Ultrapolymers

Ultrapolymers is a Pan European distribution company. Contact Ultrapolymers for availability of individual products by country.

Telephone: +32-11-57-95-57

Web: <http://www.ultrapolymers.com/>

Availability: Europe



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



Prospector Plastics Database - www.ides.com/prospector

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.

"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"

– Birgit Elvardt Bader, Production Manager, Micotron

Power Searches

Property Search – select plastics by 500 key properties and design parameters.

Alternative Resins Search – find replacement plastics within minutes.

Automotive Plastics Search – easily locate automotive approved plastics.

Curve Data – view, overlay and export curve data.



Material Data Management – www.ides.com/datasheets

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."

– Kevin Chase, Owner & President, Chase Plastics



Advertising – www.ides.com/advertise

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.

For more information, call: 800.788.4668 or 307.742.9227 ext. 220