

LNP* Verton* RV008ESV_GY7E072

Polyamide 66

SABIC Innovative Plastics



IDES | Prospector

ides.com/prospector

Technical Data

Product Description

Preliminary data for 40% long glass fiber filled, single color pellet gray, PA66

General

Material Status	• Commercial: Active
Literature ¹	• Technical Datasheet
Search for UL Yellow Card	• SABIC Innovative Plastics • LNP* Verton*
Availability	• North America
Filler / Reinforcement	• Long Glass Fiber, 40% Filler by Weight
Appearance	• Grey
Processing Method	• Injection Molding

Physical	Nominal Value Unit	Test Method
Specific Gravity	1.49 g/cm ³	ASTM D792 ISO 1183
Molding Shrinkage		ASTM D955
Flow: 24 hr	0.23 to 0.43 %	
Across Flow: 24 hr	0.90 to 1.1 %	
Water Absorption		
24 hr, 50% RH	0.93 %	ASTM D570
Equilibrium, 23°C, 50% RH	0.65 %	ISO 62

Mechanical	Nominal Value Unit	Test Method
Tensile Modulus		
-- ³	11600 MPa	ASTM D638
--	10400 MPa	ISO 527-2/1
Tensile Strength		
Yield ⁴	184 MPa	ASTM D638
Yield	195 MPa	ISO 527-2/5
Break ⁴	182 MPa	ASTM D638
Break	195 MPa	ISO 527-2/5
Tensile Elongation		
Yield ⁴	2.2 %	ASTM D638
Yield	2.3 %	ISO 527-2/5
Break ⁴	2.1 %	ASTM D638
Break	2.4 %	ISO 527-2/5
Flexural Modulus		
50.0 mm Span ⁵	11300 MPa	ASTM D790
-- ⁶	10200 MPa	ISO 178
Flexural Strength		
-- ^{6, 7}	276 MPa	ISO 178
Break, 50.0 mm Span ⁵	273 MPa	ASTM D790

Impact	Nominal Value Unit	Test Method
Notched Izod Impact		
-40°C	220 J/m	ASTM D256
23°C	250 J/m	ASTM D256
-40°C ⁸	27 kJ/m ²	ISO 180/1A
23°C ⁸	15 kJ/m ²	ISO 180/1A

LNP* Verton* RV008ESV_GY7E072

Polyamide 66

SABIC Innovative Plastics

ides.com/prospector

Impact	Nominal Value Unit	Test Method
Unnotched Izod Impact		
23°C	1100 J/m	ASTM D4812
-40°C ⁸	69 kJ/m ²	ISO 180/1U
23°C ⁸	72 kJ/m ²	ISO 180/1U
Instrumented Dart Impact		ASTM D3763
23°C, Energy at Peak Load	7.30 J	
23°C, Total Energy	16.0 J	

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load		
0.45 MPa, Unannealed, 3.20 mm	259 °C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁹	260 °C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	255 °C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁹	256 °C	ISO 75-2/Af
CLTE		ASTM E831
Flow: -30 to 30°C	0.000023 cm/cm/°C	
Transverse: -30 to 30°C	0.000058 cm/cm/°C	

Injection	Nominal Value Unit
Drying Temperature	80.0 °C
Drying Time	4.0 hr
Suggested Max Moisture	0.15 to 0.25 %
Rear Temperature	280 to 295 °C
Middle Temperature	290 to 300 °C
Front Temperature	290 to 300 °C
Processing (Melt) Temp	290 to 305 °C
Mold Temperature	95.0 to 110 °C
Back Pressure	0.150 to 0.300 MPa
Screw Speed	30 to 60 rpm

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ 50 mm/min

⁴ Type I, 5.0 mm/min

⁵ 1.3 mm/min

⁶ 2.0 mm/min

⁷ Break

⁸ 80*10*4

⁹ 80*10*4 mm

LNP* Verton* RV008ESV_GY7E072

Polyamide 66

SABIC Innovative Plastics



ides.com/prospector

Where to Buy

Supplier

SABIC Innovative Plastics

Pittsfield, MA USA

Telephone: 800-845-0600

Web: <http://www.sabic-ip.com/>

Distributor

Nexeo Solutions

Telephone: 800-531-7106

Web: <http://www.nexeosolutions.com/>

Availability: North America



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



Prospector Plastics Database - www.ides.com/prospector

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.

"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"

– Birgit Elvardt Bader, Production Manager, Micotron

Power Searches

Property Search – select plastics by 500 key properties and design parameters.

Alternative Resins Search – find replacement plastics within minutes.

Automotive Plastics Search – easily locate automotive approved plastics.

Curve Data – view, overlay and export curve data.



Material Data Management – www.ides.com/datasheets

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."

– Kevin Chase, Owner & President, Chase Plastics



Advertising – www.ides.com/advertise

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.

For more information, call: 800.788.4668 or 307.742.9227 ext. 220