

LNP™ COLORCOMP™ COMPOUND R1000SU

R-1000 HS UV
REGION AMERICAS

DESCRIPTION

LNP COLORCOMP® R1000SU is an unfilled Nylon 66 resin. Added features include: Heat Stabilized, UV Stabilized.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	75	MPa	ISO 527
Tensile Strain, yield	10	%	ISO 527
Tensile Modulus, 1 mm/min	3400	MPa	ISO 527
Flexural Stress	11	MPa	ISO 178
Flexural Modulus	3200	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	75	°C	ISO 75/Af
PHYSICAL			
Density	1.22	g/cm ³	ASTM D 792
Density	1.23	g/cm ³	ISO 1183
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	265 – 275	°C	
Front - Zone 3 Temperature	260 – 270	°C	
Middle - Zone 2 Temperature	255 – 265	°C	
Rear - Zone 1 Temperature	250 – 260	°C	
Mold Temperature	60 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	



DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.