

LNP™ THERMOTUF™ COMPOUND RF008IS

RF-1008 HI HS
REGION ASIA

DESCRIPTION

LNP THERMOTUF RF008IS is a compound based on Nylon 66 resin containing 40% Glass Fiber. Added features of this material include: High Impact, Heat Stabilized.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	168	MPa	ISO 527
Tensile Strain, break	2.7	%	ISO 527
Tensile Modulus, 1 mm/min	12500	MPa	ISO 527
Flexural Stress	274	MPa	ISO 178
Flexural Modulus	11000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	75	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	247	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow, 24 hrs (5)	0.2	%	ASTM D 955
Density	1.46	g/cm ³	ISO 1183

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.